

▶ Description



TamRez 310 is a high modulus, high strength epoxy gel designed for the surface sealing of cracks prior to injection, for surface spall repairs and bonding new concrete to old. It is moisture insensitive and will cure in a damp environment.

Clean, dry, silica sand may be added to develop a non-sag gel mortar, capable of overhead and vertical patching in layers up to two inches thick.

▶ Key Benefits

- Excellent adhesion
- Non-shrink
- Simple mix ratio ensures uniform mixing

▶ Typical Applications

- Surface sealing prior to injection
- Patching spalls, honeycombing and pop-outs
- Setting vertical and horizontal anchor bars
- Bonding similar and different materials to concrete

▶ Technical Data

TamRez 310	
Colour	Grey
Density	1.4
Mix Ratio	1:1 by volume
Pot Life (85g)	20 minutes
Gel Time (0.1mm)	25 minutes
Final Cure	1 day
Viscosity	Smooth paste
Slant Shear Bond Strength	20.6MPa
Tensile Strength, 7 days	3.0MPa
Compressive Strength	
4 hours	25MPa
24 hours	45MPa
7 days	80MPa

All technical data stated herein is based on tests carried out under laboratory conditions.

▶ Application Guidelines

As with any Epoxy Resin system, surface preparation is critical. Sandblasting, water-blasting or other mechanical means should be used to clean the concrete surfaces. All loose or unsound material must be removed. If patching, the outer perimeter of the spall should be saw cut or chipped to near vertical. Surfaces should be dry and dust free to ensure a superior bond.

This product will cure in the presence of moisture although application onto wet surfaces is not recommended. The material can be applied easily with a trowel or putty knife.

Mix the individual components Part A and Part B separately using a slow speed drill and paddle mixer for approx. 30 seconds. Add the proper ratio of Part A – resin to the Part B – Hardener in a large mixing container (plastic preferred) and mix for a further 3 minutes. Mix material for no less than 3 minutes. Longer mixing times may be required in cooler weather. The material can be applied easily with a trowel or putty knife.

TamRez 310

Universal Epoxy Putty



▶ Subsequent Finishes / Ongoing Maintenance

All equipment and tools are to be cleaned using TamRez Cleaner.

▶ Packaging

TamRez 310 is supplied in 2 litre and 12 litre packs. Packaging size may vary subject to local regulations and requirements.

▶ Storage

TamRez 310 should be stored at room temperature (min 10°C and max 35°C), kept dry and out of direct sunlight. If these conditions are maintained and the product packaging is unopened, then a shelf life of 1 year can be expected.

▶ Health & Safety

TamRez 310 should only be used as directed. We always recommend that the Health & Safety data sheet is carefully read prior to application of the material. Our recommendations for protective equipment should be strictly adhered to for your personal protection. The Health & Safety data sheet is available upon request from your local TAM International representative.

www.taminternational.com

TAM Australia
☎ +61 8 8340 4166

TAM Hong Kong
☎ +852 2690 3723

TAM India
☎ +91 92 7222 5905

TAM Singapore
☎ +65 6296 0364

TAM Taiwan
☎ +886 49 2263 066

TAM UK
☎ +44 2476 253098